

Effect of long-term aging on low-temperature cracking of asphalt mixtures using mechanical and thermodynamic methods

Pouya Moradi¹, Hamid Shirmohammadi², Gholam Hossein Hamedi^{3,*}

¹M.Sc Student, Department of Civil Engineering, Urmia University, Urmia, Iran. Email: moradipouya144@gmail.com

²Associate Professor, Department of Civil Engineering, Urmia University, Urmia, Iran. Email: h.shirmohammadi@urmia.ac.ir

^{3,*} Assistant Professor, Department of Civil Engineering, University of Guilan, P.O. Box 3756, Rasht, Iran (corresponding author). E-mail: hamedi@guilan.ac.ir, Tell:00989127595367, Fax: 0981333690274

ABSTRACT

One of the common phenomena in cracking of asphalt pavements is thermal cracks or cracks due to low temperature, which occur in cold regions and accelerate the distresses of road structures. Numerous different factors affect the behavior of asphalt mixtures at low temperatures. The factors affecting heat cracking in asphalt concrete pavements are generally divided into three categories: materials, environment and geometry of the pavement structure. Factors related to materials in the occurrence of thermal cracks include bitumen, type and aggregate granulation, percentage of bitumen and percentage of air pores. One of the most important factors affecting the occurrence of bitumen on the occurrence of thermal cracks is the aging of bitumen or in other words the age of pavement. As a result, bitumen aging has a direct effect on pavement performance. In most existing studies to investigate the aging performance of asphalt mixes, the results of mechanical tests are used to investigate the thermal cracking potential of an asphalt mix and less attention is paid to the basic properties of materials that are important in the event of this cracking. Accordingly, the present study investigates the effect of aging on thermal cracking of 12 different compositions of asphalt mixtures through mechanical methods and free surface energy (SFE), which is based on the main properties of the material. Thermal cracking of asphalt mixtures has been evaluated by performing semi-circular bending mechanical tests and thermodynamic tests by determining the SFE components of bitumen and aggregates. The results showed that the parameters of fracture energy and fracture toughness, which are known as indicators of sensitivity of asphalt mix to thermal cracking, for aged asphalt mixtures between 6.3-13.7% and between 6.5-10.7%, respectively. The results of SFE tests show that aging causes an increase in the non-polar component between 1.3-1.5% and a decrease in the acidic and basic free energy components of bitumen between 41.1-53.4% and between 334.2-349.6%, respectively. These results have increased the amount of free cohesive energy from 0.63 to 1.03 (ergs/cm²). Also, aging reduces the free energy of bitumen-aggregate adhesion with a maximum reduction of 2.61 (ergs/cm²). This means that aging reduces the coverability of bitumen on the aggregate surface and the resistance to fracture at the bitumen-aggregate interface.

KEYWORDS:

Hot asphalt mix, Thermal cracking, Aging, Semicircular bending test, Surface free energy

Introduction

Aging of bitumen occurs during the production process of asphalt mix and during operation, which is exposed to environmental conditions [1]. The first stage of aging, called short-term aging, usually occurs at a high rate. Short-term aging occurs when bitumen and aggregates are heated to high temperatures and mixed together. At the end of this stage, the asphalt mixture is moved to the project site, spread and compacted, which is considered as part of short-term aging. The second stage of aging, known as long-term aging, occurs much faster than the first stage during the operation period. After applying the asphalt mixture, aging usually occurs for 2-3 years so that the specific gravity of the asphalt mixture reaches its maximum and after this time no more compaction occurs. Most of the aging occurs at this time, but usually the aging process continues between 8 and 12 years [2]. Aging significantly affects the mechanical properties of asphalt mixtures (including hardness modulus, phase angle, etc.) and consequently the performance of asphalt mixtures. Therefore, it is necessary to know the characteristics of the aged asphalt mixture in order to properly plan the mixing of asphalt layers and pavement structures [3].

In recent years, the use of surface free energy method as one of the valid methods in the science of adhesion in the occurrence and modeling of moisture failure of asphalt mixtures has been used, which has interesting results about the process of this failure and the role of effective parameters in it [4,5]. However, the use of this theory to investigate the occurrence of low temperature cracking has not been considered. Given the close relationship between the occurrence of thermal cracking and the theory of thermodynamics, it can be expected that its use can be useful in identifying the effective parameters in the occurrence of cracking of asphalt mixtures. Accordingly, in this study, using the surface free energy method, the effect of long-term aging on the thermal cracking potential of asphalt mixtures is investigated and the results of this theory are compared with the results of mechanical tests. The most important objectives of the present study are:

- The effect of aging on bitumen surface free energy components and cracking in mastic,
- The effect of aging on the free energy of bitumen-aggregate adhesion and cracking at the bitumen-aggregate contact surface,
- Investigation of the effect of aging on the results of performance tests of asphalt mixtures at low temperatures,
- Relationship between the results of thermodynamic parameters and semicircular bending of asphalt mixtures

Methodology

In this study, two types of bitumen with a degree of performance of PG 58-22 and PG 64-16 and a polymer additive called polyethylene with very high molecular weight (UHMWPE) in two percent of bitumen mass, along with two types of base aggregates (limestone and granite) Used. The research method algorithm used in this research is presented in Figure 1. As can be seen, experiments to determine the surface free energy on bitumen and aggregates are performed separately in different states, and mechanical tests are performed to determine the potential for low-temperature cracking on asphalt mixtures.

In this research, UHMWPE polymer has been used to improve bitumen. For this purpose, a high-speed agitator was used. The mixing process was continued for 25 minutes in order to modify the bitumen so that the additive particles were evenly distributed in the bitumen space. In order to prevent the temperature of the bitumen from decreasing next to the bitumen container, the heater surrounding the bitumen container has been used. Due to the fact that the modified bitumens may have suffered some aging at the mentioned temperature and time, this process has also been performed for the control bitumens so that the effect of aging in analyzing the results and comparing the results does not cause errors.

Results and Discussion

The results of measurements of surface free energy components of base and modified bitumens in the form of unaged and aged are presented in Table 6. The results related to the acidic components and the surface free energy base in Table 6 show that the bitumens in the ground state show more acidic properties compared to the basic properties. The use of UHMWPE has increased the free energy component of the surface and decreased its acid component. The aging process has caused the acidic component of surface free energy to increase significantly and its alkaline component to decrease slightly. This can have a negative effect on the adhesion due to the polar cohesions formed between the aged bitumen and the aggregates such as limestone.

The results related to the polar component of surface free energy of aged and aged bitumens in Table 6 show that PG 28-22 bitumen has a higher polarity component compared to PG bitumen 16-64. Polar cohesions usually do not have good strength against moisture but have good resistance to environmental conditions. Oxidation with high temperature increases the polarity of molecules and thus increases the aggregation and cohesion of these molecules. The use of UHMWPE additive also increases the polar component of the surface free energy of the modified bitumen. The increasing polar component of surface free energy is also observed due to aging in the modified bitumens.

The results show that the polar cohesions of bitumen play a very important role in the performance of bitumen against its failure. Non-polar cohesions are usually due to the cohesion between aromatic oils and bitumen saturation. As a result of aging, it is observed that the percentage of these oils in bitumen decreases. This reduces the non-polar component of the surface free energy of the aged bitumen. Reduction in the non-polar component of the bitumen surface free energy, in addition to increasing the viscosity and hardness, reduces the non-polar cohesions formed between the bitumen and the aggregates. These joints are very effective in the resistance of the asphalt mixture to exposure.

The results related to the failure parameter in different asphalt mixtures at low, medium and high temperatures are presented in Figures 4-6, respectively. The data presented in these figures show that aging has significantly reduced the fracture energy in samples of asphalt mixtures. In fact, the aging of bitumen increases the amount of bitumen cohesion energy but decreases the bitumen-aggregate adhesion energy. Given that the fracture energy is the sum of the absorbed energy from the moment of loading to the moment of failure, it can be said that aging has caused the ability to absorb stress by the asphalt mixture. This is present in all samples of asphalt mixtures, where aging causes a reduction in the amount of fracture energy, but in samples made with bitumen PG 58-22 is more. In fact, these bitumens have better performance in cold weather conditions than PG bitumen 16-64. On the other hand, the amount of oil in these bitumens is more than PG bitumen 16-64. This causes the aging to cause a greater performance difference between the control and aged bitumens in samples containing PG 58-22 bitumen than PG 64-6 bitumen.

By comparing the results of the amount of fracture toughness in the aged and aged samples, it can be seen that aging has caused the value of the fracture toughness parameter to be significantly reduced. In fact, aging causes the percentage of asphaltene in the bitumen structure to increase and the lighter parts of the bitumen to evaporate or become larger molecules. These changes cause the aged bitumens to have less flexibility. Cold weather also intensifies the brittleness properties of bitumen. The result is low-temperature cracking in pavements that are several years old and exposed to thermal cycles or a very short cold period. Also, the comparison of the results between PG 58-22 and PG 64-6 bitumens shows that the use of PG 58-22 bitumen has caused the asphalt mixtures to have a better performance against low temperature cracking. This can be attributed to the higher percentage of oils in the bitumen structure of PG 58-22.

Conclusions

The aging process and its effect on the properties of asphalt mixtures have been studied in several studies. However, the study of the effect of aging on the basic properties of materials based on the concepts of surface free energy method can provide results that provide a better view of the process of various failures in asphalt mixtures and provide methods to prevent these failures for researchers and design engineers. Accordingly, in this study, the role of long-term aging on bitumen surface free energy parameters and its effect on cohesion failure in bitumen and adhesion failure at the bitumen-aggregate contact surface have been investigated. Also, an attempt has been made to investigate the cracking potential of low temperature at three different temperatures using the semicircular bending method and the results of this experiment are compared with the results of the surface free energy method. The most important results obtained in this study are:

- Aging has caused the volatile oils of bitumen to evaporate and the concentration of heavy and polar parts such as asphalt to increase. This has led to an increase in the polar and non-polar components of the surface free energy of aged bitumens compared to unaged bitumens. Also, aging has caused an increase in the acidic component and a decrease in the free surface energy component of the bitumen used in this study.
- Aging of bitumen has caused a significant increase in the amount of free cohesive energy of this material. The main reason for this can be a decrease in the percentages of aged bitumen oil and an increase in its asphaltene concentration.

References

- [1] E. Brown, P.S. Kandhal, F.L. Roberts, Y.R. Kim, D.-Y. Lee, T.W. Kennedy, Hot mix asphalt materials, mixture design, and construction, NAPA Research and Education Foundation, Lanham, MD, (2009).
- [2] C.J. Glover, A.E. Martin, A. Chowdhury, R. Han, N. Prapaitrakul, X. Jin, J. Lawrence, Evaluation of binder aging and its influence in aging of hot mix asphalt concrete: literature review and experimental design, Texas Transportation Institute, 2009.
- [3] D.K. Paul, O. Sirin, E. Kassem, Laboratory investigation of asphalt mixture aging, in: Proceedings of 6th Eurasphalt & Eurobitume Congress, 2016.
- [4] N. Esmaeili, G.H. Hamed, M. Khodadadi, Determination of the stripping process of asphalt mixtures and the effective mix design and SFE parameters on its different phases, Construction and Building Materials, 213 (2019) 167-181.
- [5] A. Abdelaziz, C.-H. Ho, M. Snyder, Evaluating the Influence of Polymer Modified Asphalt Binders on Low Temperature Properties, in: MATEC Web of Conferences, EDP Sciences, 2018, pp. 05012.

↑ please level both columns of the last page as far as possible. ↑